DuPont[™] Tyvek[®] StructureGuard Technical Datasheet



Application: Flexible sheets for water proofing – Part 1: Underlays for discontinuous roofing EN 13859-1: 2010

Style name 1560B				Language	English	
Type of carrier	HDPE			Applicable for	UK, Ireland	
PROF	PERTY	METHOD	UNITS	NOMINAL	MINIMUM	MAXIMUM
F	UNCTIONALITY: WA	TER VAPOUR TRANSMISSI	ON, WATER TIGHTN	IESS, WEATHER DUR	ABILITY, FIRE CLASS	
Water vapour transmission (sd)		EN ISO 12572 (C)	m	0,015	0,005	0,03
Temperature resistance		-	°C	-	-40	+100
Flexibility at low temperature		EN 1109	°C	-	-	-40
UV exposure		-	months	-	-	4
Product- / Functional layer thickness		-	mm	0,175 / 0,175	-	-
Water tightness		EN 1928 (A)	class	W1	-	-
Water column		EN 20811	m	2	1,8	-
Reaction to fire		EN ISO 11925-2	class	E (*)	-	-
		PHYSICAL AND	MECHANICAL PRO	PERTIES		
Mass per unit area		EN 1849-2	g/m²	58	55	61
Maximum tensile force (MD)		EN 12311-1	N/50mm	165	145	185
Elongation at max. tensile force (MD)		EN 12311-1	%	9	7,5	10,5
Maximum tensile force (XD)		EN 12311-1	N/50mm	135	115	165
Elongation at max. tensile force (XD)		EN 12311-1	%	14,5	12	17
Resistance to tearing MD (nail shank)		EN 12310-1	Ν	60	50	70
Resistance to tearing XD (nail shank)		EN 12310-1	Ν	60	50	70
		PROPER	TIES AFTER AGEINO	G		
Artificial ageing by UV and heat:		EN 1297 & EN 1296	residual value			
Water tightness		EN 1928 (A)	class	W1	-	-
Maximum tensile force (MD)		EN 12311-1	%	90	-	-
MD elongation at max. tensile force		EN 12311-1	%	85	-	-
Maximum tensile force (XD)		EN 12311-1	%	90	-	-
XD elongation at max. tensile force		EN 12311-1	%	75	-	-
		ADDIT	ONAL PROPERTIES			
ength (customer related, expressed in m)		EN 1848-2	deviation in %	0	0	-
Width (customer related, expressed in mm)		EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness		EN 1848-2	mm/10m	-	-	30
Dimensional stability (MD & XD)		EN 1107-2	%	-	-	1
Resistance to penetration of air		EN 12114	m³/(m² h 50Pa)	-	-	0,25
Windtight		-	-	yes	-	-

(*): on mineral wool and wood

The product mentioned above, in our opinion, fulfils the criteria of being classified as 'article' (REACH, Art. 3.3). There are no substances intended to be released from this product under normal or reasonably foreseeable conditions of use. The above article to our current knowledge does not contain substances, above the legal threshold, that are on the 'Candidate List' of Substances of Very High Concern (SVHC) as published on the ECHA website.



DuPont (UK) Limited HERE, 470 Bath Road, Arnos Vale, Bristol , BS4 3AP tyvek.construction@dupont.com

Tel +44 (0) 117 452 9050

www.building.dupont.co.uk

Effective date: 15/12/2023 First CE: 18/07/2006



Some test methods are modified according to the EN 13859-12010 & EN 13859-22010 and/or according to the DuPont ISO 90012015 certified quality system (for details please contact your regional DuPont representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 0F THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the subability of our products for any application other than the applications in secure ind-use conditions, DuPont makes no warranties and assumes no liabilities in commetion with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.