

DuPont™ Tyvek® UV Facade Technical Datasheet



Application: Flexible sheets for water proofing – Part 2: Underlays for walls EN 13859-2: 2010 walls with open joints (1)

Application: Flexible sheets for water proofing – Part 1: Underlays for discontinuous roofing EN 13859-1: 2010

Style name **2524B**

Language **English**

Type of carrier **HDPE and PP composite**

Applicable for **UK, Ireland**

PROPERTY	METHOD	UNITS	NOMINAL	MINIMUM	MAXIMUM
FUNCTIONALITY: WATER VAPOUR TRANSMISSION, WATER TIGHTNESS, WEATHER DURABILITY, FIRE CLASS					
Water vapour transmission (sd)	EN ISO 12572 (C)	m	0,035	0,02	0,045
Temperature resistance	-	°C	-	-40	+80
Weather resistance					
Full UV exposure (as standard underlay)	-	months	-	-	6
Full UV exposure (for walls with open joints before installation of facade elements)	-	months	-	-	4
Flexibility at low temperature	EN 1109	°C	-	-	-40
Product- / Functional layer thickness	-	mm	0,630 / 0,220	-	-
Water tightness	EN 1928 (A)	class	W1	-	-
Water column	EN 20811	m	3	-	-
Reaction to fire	EN ISO 11925-2	class	E	-	-
PHYSICAL AND MECHANICAL PROPERTIES					
Mass per unit area	EN 1849-2	g/m ²	195	180	210
Maximum tensile force (MD)	EN 12311-1	N/50mm	390	340	440
Elongation at max. tensile force (MD)	EN 12311-1	%	13	10	16
Maximum tensile force (XD)	EN 12311-1	N/50mm	320	260	380
Elongation at max. tensile force (XD)	EN 12311-1	%	19	14	24
Resistance to tearing MD (nail shank)	EN 12310-1	N	310	230	390
Resistance to tearing XD (nail shank)	EN 12310-1	N	370	260	480
PROPERTIES AFTER AGEING					
Artificial ageing by UV and heat:	EN 1297 & EN 1296	residual value	(1)		
Water tightness	EN 1928 (A)	class	W1	-	-
Maximum tensile force (MD)	EN 12311-1	%	70	-	-
MD elongation at max. tensile force	EN 12311-1	%	60	-	-
Maximum tensile force (XD)	EN 12311-1	%	70	-	-
XD elongation at max. tensile force	EN 12311-1	%	60	-	-
ADDITIONAL PROPERTIES					
Length (customer related, expressed in m)	EN 1848-2	deviation in %	0	0	-
Width (customer related, expressed in mm)	EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness	EN 1848-2	mm/10m	-	-	30
Dimensional stability (MD & XD)	EN 1107-2	%	-	-	1
Water tightness of seams	EN 13859-1: 2010	pass / no pass	pass	-	-
Resistance to penetration of air	EN 12114	m ³ /(m ² h 50Pa)	-	-	0,1
Windtight	-	-	yes	-	-
Max width of joints (vertical & horizontal)	-	cm	-	-	A < 3 cm
Min width of facade elements	-	-	-	-	B >= 2 x A


(1) according to EN 13859-2: 2010 for walls with open joints, artificial aging by UV is 5000 hrs (standard wall/roof application is 336 hrs)

The product mentioned above, in our opinion, fulfils the criteria of being classified as 'article' (REACH, Art. 3.3). There are no substances intended to be released from this product under normal or reasonably foreseeable conditions of use. The above article to our current knowledge does not contain substances, above the legal threshold, that are on the 'Candidate List' of Substances of Very High Concern (SVHC) as published on the ECHA website.



Effective date: 15/12/2023

First CE: 21/12/2007



DuPont (UK) Limited
HERE,
470 Bath Road, Arnos Vale,
Bristol, BS4 3AP
tyvek.construction@dupont.com

Tel +44 (0) 117 452 9050

www.building.dupont.co.uk

Some test methods are modified according to the EN 13859-1:2010 & EN 13859-2:2010 and/or according to the DuPont ISO 9001:2015 certified quality system (for details please contact your regional DuPont representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.