



TD0127SWH00

Tyvek® 400 DualFinish

DuPont™ Tyvek® 400 DualFinish. Hooded coverall. Tyvek® at the front and large breathable SMS back. Stitched external seams in blue. Elasticated wrists, ankles and face. Thumb Holes. Elasticated waist (stitched-in). Zipper and flap. White.

Name	Description
Full Part Number	TD0127SWH00
Fabric/Materials	Tyvek® 400 / SMS
Design	Hooded coverall with elastics, Tyvek® front, SMS back
Seam	Stitched (external), blue
Color	White
Sizes	SM, MD, LG, XL, 2X, 3X, 4X
Quantity/Box	25 per box, bulk packed.

FEATURES & PRODUCT DETAILS

DuPont™ Tyvek® 400 DualFinish. Hooded coverall combining Tyvek® with a SMS back panel from shoulders to ankle. Available in sizes SM to 4X. 2-piece hood. Elasticated face, wrists, waist and ankles. Stitched external seams in blue. Thumb hole on sleeve. White.

The Tyvek® front provides an ideal balance of protection, durability and comfort. It is permeable to both air and water vapour, yet repels water-based liquids and aerosols. It offers an excellent barrier against fine particles and fibres down to 1 micron in size. It is ultra-low-linting and antistatically treated. Silicon non-added.

The large, breathable back panel, made of SMS nonwoven, offers lower protection against particles (down to 3 microns in size) and light water-based splashes, yet high levels of comfort.

Tyvek® 400 DualFinish is designed for specific applications that demand comfort while helping to provide protection from frontal exposure during, paint spraying or any work involving composite materials, glass manufacturing, and utilities.

- Certified according to Regulation (EU) 2016/425
- Chemical protective clothing, Category III, Type 5 and 6
- Antistatic treatment (EN 1149-5) - on inside
- Stitched external seams for enhanced protection against penetration from the outside to the inside of the garment
- Nylon zipper with flap

SIZES

Product Size	Article Number	Additional info
SM	D14681302	
MD	D14681312	
LG	D14681321	
XL	D14681332	
2X	D14681349	
3X	D14681353	
4X	D14681365	

Physical Properties



Data relating to mechanical performance of the fabrics used in DuPont chemical protective clothing, listed for the selected garment according to the test methods and relevant European standard, if applicable. Such properties, including abrasion and flex-cracking resistance, tensile strength and puncture resistance can help in the assessment of protective performance.

Property	Test Method	Typical Result	EN
Abrasion Resistance ⁷	EN 530 Method 2	>10 cycles	1/6 ¹
Basis Weight	DIN EN ISO 536	41.5/43 g/m ² ⁵	N/A
Colour	N/A	White	N/A
Flex Cracking Resistance ⁷	EN ISO 7854 Method B	>1000 cycles	1/6 ¹
Puncture Resistance	EN 863	>5 N	1/6 ¹
Resistance to water penetration	DIN EN 20811	>10/3 kPa ⁵	N/A
Tensile Strength (MD)	DIN EN ISO 13934-1	>30 N	1/6 ¹
Tensile Strength (XD)	DIN EN ISO 13934-1	>30 N	1/6 ¹
Thickness	DIN EN ISO 534	140/- μm ⁵	N/A
Trapezoidal Tear Resistance (MD)	EN ISO 9073-4	>10 N	1/6 ¹
Trapezoidal Tear Resistance (XD)	EN ISO 9073-4	>10 N	1/6 ¹

1 According to EN 14325 2 According to EN 14126 3 According to EN 1073-2 4 According to EN 14116 12
 According to EN 11612 5 Front Tyvek ® / Back 6 Based on test according to ASTM D-572 7 See Instructions for
 Use for further information, limitations and warnings > Larger than < Smaller than N/A Not Applicable STD DEV
 Standard Deviation

GARMENT PERFORMANCE



Information relating to the protective performance of a garment according to European standards where applicable. Includes important characteristics such as protection against radioactive contamination, seam strength and shelf life. Inward leakage and resistance to penetration by liquids, according to the relevant Type classification, are also detailed.

Property	Test Method	Typical Result	EN
Seam Strength	EN ISO 13935-2	>30 N	1/6 ¹
Shelf Life ⁷	N/A	2 years ⁶	N/A
Type PB 6: Partial Body Protection	EN ISO 13982-2	Pass	N/A

1 According to EN 14325 3 According to EN 1073-2 12 According to EN 11612 13 According to EN 11611 5 Front Tyvek® / Back 6 Based on test according to ASTM D-572 7 See Instructions for Use for further information, limitations and warnings 11 Based on the average of 10 suits, 3 activities, 3 probes > Larger than < Smaller than N/A Not Applicable * Based on lowest single value

COMFORT



The comfort of a protective garment during use is largely determined by its weight, its permeability to vapour and air (breathability) and insulating properties. Data on these attributes is provided according to test method and, as with other data, can be compared by garment.

Property	Test Method	Typical Result	EN
Air Permeability (Gurley method)	ISO 5636-5	Yes/- ⁵	N/A
Air Permeability (Gurley method)	ISO 5636-5	< 45 /- s ⁵	N/A

2 According to EN 14126 5 Front Tyvek® / Back > Larger than < Smaller than N/A Not Applicable

PENETRATION AND REPELLENCY



A specific test method, EN ISO 6530, is used to measure the indexes of penetration, absorption and repellency of protective clothing material exposed to liquid chemicals. Results listed here reflect the penetration resistance and repellency of DuPont fabrics to 30% sulphuric acid and 10% sodium hydroxide.

Property	Test Method	Typical Result	EN
Repellency to Liquids, Sodium Hydroxide (10%)	EN ISO 6530	>80 %	1/3 ¹
Repellency to Liquids, Sulphuric Acid (30%)	EN ISO 6530	>95 %	3/3 ¹
Resistance to Penetration by Liquids, Sodium Hydroxide (10%)	EN ISO 6530	<10 %	1/3 ¹
Resistance to Penetration by Liquids, Sulphuric Acid (30%)	EN ISO 6530	<5 %	2/3 ¹

¹ According to EN 14325 > Larger than < Smaller than

Warning

- The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.
- This garment and/or fabric are not flame resistant and should not be used around heat, open flame, sparks or in potentially flammable environments.